


# Technical data sheet

## StoSilent Board 210

Acoustic panel made of expanded glass granulate for suspended ceiling and wall structures



### Characteristics

#### Areas of application

- interior
- for suspended ceiling and wall structures
- fixing with screws and adhesive

#### Properties

- non-combustible
- reaction to fire (class) in accordance with EN 13501-1: A2-s1, d0 (panel with coating)
- up to 200 m<sup>2</sup> possible without expansion joint (max. side length: 20 m)
- reduction in the reverberation time and noise level
- improved ability to concentrate
- improvement in speech intelligibility
- rated sound absorption factor  $\alpha_w$  of up to 0.55 depending on the suspension height
- low weight and high stiffness
- low moisture-induced and thermal expansion

#### Format

- board edge: sharp-edged / coated
- length x width x thickness
- 1200 x 800 x 25 mm

#### Appearance

- coating: StoSilent Decor M or StoSilent Decor MF on StoSilent Decor M

#### Information/notes

- use in brine or saltwater swimming pools only on request
- not suitable in splash water zones
- not suitable for radii < 10 m and areas exposed to mechanical stress
- observe installation instructions

# Technical data sheet

## StoSilent Board 210

### Technical data

Criterion	Standard / test regulation	Value/ Unit	Notes
Diffusion-equivalent air layer thickness	EN ISO 7783-2	0.19 m	with coating
Reaction to fire (class)	EN 13501-1	A2-s1, d0	with coating
Rated value of thermal conductivity $\lambda$	TIAP-655 based on EN 12667	0.087 W/(m*K)	with coating
Area weight		9.0 kg/m <sup>2</sup>	
Apparent density		361 kg/m <sup>3</sup>	
Sound absorption degree $\alpha_w$		0.55	With coating; can vary depending on the suspension height and damping

The characteristic values stated are average values or approx. values. We use natural raw materials in our products, which means that the stated values can vary slightly in the same delivery batch; this does not affect the suitability of the product for its intended use.

### Substrate

#### Requirements

The substrate must be firm, dry, clean, and load-bearing.

# Technical data sheet

---

## StoSilent Board 210

### Application

**Application temperature**      Lowest application and substrate temperature: +12 °C at max. 70 % relative air humidity; installation after adjusting the equilibrium humidity in the room. Rapid shock-type heating or cooling during installation and drying can induce crack formation.

### Consumption

Execution	Approx. consumption
	1.00 m <sup>2</sup> /m <sup>2</sup>

The stated consumption values are only to be used as a guide. If required, precise consumption values plus cuttings should be determined on the project.

### Coating procedure

metal sub-construction in accordance with EN 13964 with vernier hangers; fine grid bonded with StoSilent Profile Tape

StoSilent Board 210

System adhesive:  
StoSilent Fix (approx. 0.3 kg/m<sup>2</sup>)

System filler:  
StoSilent Plan (approx. 0.2 kg/m<sup>2</sup>)

Finish:  
StoSilent Decor M (three spray application cycles with a total of 2.7 kg/m<sup>2</sup>)

### Application

The boards should be fixed in longitudinal direction to the carrier profiles to which the StoSilent Profile Tape has been applied. Align longitudinal joints toward the incidence of light. Install the boards with transverse joints that are offset by at least 400 mm.

Fix the boards with phosphate-treated, quick-assembly screws with a needle point (TN form in accordance with DIN 18182) starting from the middle of the board or a corner in order to avoid compressions. When fixing the screws, press the board firmly onto the sub-construction. Insert the screws approx. 15 mm from the board edge and sink the screw heads to a depth of approx. 1 mm. Ensure a distance of 200 mm between the screws.

The bonding edges must be free from dust.

At the factory, a sealant is applied to the board edges to make them flow-proof. Dust off, paint, or waterproof all edges cut subsequently or on site using the system paint or system adhesive in order for the finished surface to appear

# Technical data sheet

---

## StoSilent Board 210

homogeneous (closed pores, no visible expanded glass).  
 Mix the system adhesive (StoSilent Fix) in accordance with the application guidelines.  
 After fixing the board, apply the system adhesive to the edges (e.g. with a Japanese spatula or cartridge).  
 Press the following board onto the fine grid of the sub-construction, then push it against the already installed boards and fix it with screws.

Use an electrical keyhole saw, handsaw or surform to cut, grind or plane the material.

System connections:  
 to enable pressure equalisation between the ceiling cavity and the used space, ensure rear ventilation either through an open, all-around joint or openings in the ceiling. The proportion of the ceiling opening should account for at least 0.8 % of the ceiling surface area. In most cases, this is achieved by an open all-around joint of 2 cm.

---

### Cleaning the tools

Remove dust after use.

---

### Indications, recommendations, special information, miscellaneous

Please observe the general Sto application guidelines for Sto acoustic panel systems. They are available from Sto SE & Co. KGaA.

Installation/coating must only be carried out after prior instruction.

If the fine grid (e.g. when retrofitting ceiling installations) is cut through, create additional transition points. Seal the cavities in adjacent walls to prevent low-pressure ceilings.

Structural expansion joints must be incorporated.

---

### Delivery

#### Colour shade

visible side: white (approx. RAL 9010), rear side: grey (approx. RAL 7039)

---

#### Packaging

pallet

---

### Storage

#### Storage conditions

Store in dry and frost-free conditions. Product is sensitive to shocks, do not subject it to loads or stress.

# Technical data sheet

## StoSilent Board 210

---

### Certificates/approvals

Test report No. 14-002-789 B StoSilent Board 210 with StoSilent Decor - ASTM E84  
Fire behaviour test in accordance with ASTM E84

---

M 10 0960/5 Page 1 StoSilent Distance A2 - StoSilent Board 210 - StoSilent Decor  
M - Build-up E-200  
Determination of the sound absorption factor in accordance  
with EN ISO 354

---

M 10 0960/5 Page 2 StoSilent Distance A2 - StoSilent Board 210, with open  
shadow gap - StoSilent Decor M - Build-up E-200 (variant)  
Determination of the sound absorption factor in accordance  
with EN ISO 354

---

M 10 0960/5 Page 3 StoSilent Distance A2 - StoSilent Board 210, with open  
shadow gap + MiWo - StoSilent Decor M - Build-up E-200  
(variant)  
Determination of the sound absorption factor in accordance  
with EN ISO 354

---

### Identification

**Product group** Acoustic panel

---

**Safety** Please observe the safety data sheet

---

## Technical data sheet

---

# StoSilent Board 210

### Special notes

The information or data in this technical data sheet serves to ensure the product's intended use, or its suitability for use, and is based on our findings and experience. Nevertheless, users are responsible for establishing the suitability of the product for its intended use.

Applications other than those explicitly mentioned in this technical data sheet are only permissible after prior consultation. Where no approval is given, such applications are at the risk of the user. This applies particularly to combinations with other products.

When a new technical data sheet is published, all previous technical data sheets are no longer valid. The latest version is available on the Internet.

Sto SE & Co. KGaA  
Ehrenbachstr. 1  
79780 Stühlingen / Germany  
Phone: +49 7744 57-0  
Fax: +49 7744 57-2178  
Infoservice.export@sto.com  
www.sto.com